



**TM 133 (Nickel Boron)** is a state of the art coating providing a very low coefficient of friction in wear applications without reduction of hardness experienced with other coatings. TM 133 is an engineered surface deposit coating which is readily applied to a variety of substrates that produce an extremely slick, abrasion & wear resistant surface. This coating has a columnar structure with a nodular surface that provides it with superior abrasion resistance and superior resistance to fretting galling. TM 133 has three times the wear resistance of a Mid Phosphorus Nickel. TM 133 has a lower coefficient of friction than coatings containing Teflon. Unlike Teflon, which will start to decompose at 600° F, TM 133 will maintain its integrity up to the melting point of the deposit.

## USER BENEFITS

**Uniform Coating**  
**Pleasing Light Gray Color**  
**Excellent Release Properties**

**Extreme Abrasion Resistance**  
**Can Be Applied to any Metal**

## PROPERTIES

Hardness (VHN)

As Plated

Heat Treated

Chemical Composition

Nickel

Thallium

Boron

Melting Range

Thickness Controllability

Wear Resistance

(Falex Test per ASTM D 2714)

Corrosion Resistance

(.001" Deposit ASTM-117)

## TYPICAL VALUE

63-65 RC

Up to 74 RC

89-95%

2.5-6.0%

2.5-5.0%

1922-2102 F/ 1050-1150 C

.00001-.010"

Weight Loss in grams: .0002"

200 Hours (Can be improved considerably with an undercoat of TM 103)

This deposit can be used as a replacement for Hard Chrome, Carbide and even Titanium Nitride

Uncontrolled Copy 09/06/05gm



PO Box 1266 Dayton, Ohio 45403 (937)253-5311